

**DESCRIPTION**

Wall primer, free from alkylphenol ethoxylates (APEO free), plasticisers and coalescents, formulated with acrylic resins in aqueous dispersion with a special microemulsion technology that guarantees secure adhesion on various types of substrate, with insulating and consolidating capacity. It guarantees even absorption and hence a uniform finish and excellent adhesion for subsequent coats. It is mainly formulated for exterior treatments.

**COMPOSITION**

Product formulated with acrylic resins in an aqueous dispersion free of ethoxylated alkylphenols (APEO free), plasticisers and coalescents.

**PRODUCT PROPERTY**

	<b>Value</b>	<b>Method</b>
<b>WATER VAPOUR PERMEABILITY</b>	Excellent	
<b>ADHESION TO SUBSTRATES IN BUILDINGS</b>	Excellent	interior PF16
<b>Solid by weight</b>	11-15%	interior PF25
<b>Drying</b>	Dry to recoat 5-8h Fully 5 days	interior PF2

**SPECIFICATION DATA**

	<b>Value</b>	<b>Method</b>
<b>Density</b>	950-1050 g/l	interior PF3

**SHELF LIFE**

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

**COLOUR RANGE**

Colourless.

**TYPICAL USE**

Apply directly as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat. Can be recoated with acrylic finishes, either elastomeric, such as *K81*, *Fasadecap line* products.

**TOOLS**

Roller, Brush, Spray.

**THINNING**

Ready to use.

**COVERAGE**

8-10 m<sup>2</sup>/l per coat

**APPLY**

+5°C +30°C

**SPECIFICATION ITEM**

Colourless masonry primer containing colloidal resins in aqueous dispersion, at an average consumption rate of 110 ml/m<sup>2</sup>.

**INSTRUCTIONS**

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The

# ACRILFIX SPECIAL

Micronized water-based transparent primer for exterior

specification data and technical information have been calculated at +23 °C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.