

DESCRIPTION

Skim coat for interiors with decorative and filling function. Adheres to various materials and is distinguished by good workability.

Paste composed of specially designed fillers and binders which make the product extremely hard and fast drying. This composition guarantees easy skimming, sandpapering and polishing. Thanks to these features, the filler *Décor Stucco* is excellent for obtaining a "Venetian style" coating.

COMPOSITION

Based on synthetic resins in water dispersion and selected aggregates.

PROPERTY OF THE PRODUCT

		Method
Adhesion	GOOD	interior PF16
Drying time	Recoatable 12 h Complete 5 days washing 5 days	interior PF2
Solid by weight	76-80 %	interior PF25
Specific weight	2100 - 2200 g/L	

SHELF LIFE

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

COLOUR RANGE

White.

TYPICAL USE

It is suitable for decorating and protecting various substrates, new or undergoing maintenance, such as plaster of various compositions (cementitious, lime-based, pre-mixed), concrete and fibre cement, plasterboard, stucco skim coats and old paints in all cases where a product with a particular aesthetic result is required.

Tools are washed with water immediately after use.

TOOLS

Stainless steel trowel, stainless steel spatula.

THINNING

Ready to use.

COVERAGE

0.9-1.1 m²/kg

APPLY

+5°C +30°C

COATING SYSTEM

Cement plasters, cement-lime plasters, hydraulic lime plasters, premixed new plasters

1. Remove traces of dust, fill with Stucco Light;
2. Perform skimming with Decor Stucco to even out the substrate;
3. After approximately 12 hours, apply a further layer to level the surface;
4. After about 12 hours, sand to remove any imperfections; then remove dust and a

Reinforced concrete, precast concrete, gypsum plaster skim coats, plasterboard, old synthetic paints

1A -Precoat with Unifix Fine and proceed as in points 2, 3, 4.

SPECIFICATION ITEM

Skim coat for interiors with decorative and filling function, "Venetian stucco" style, dry polishable, to be applied in successive skim coats with marks using an 8 cm spatula at an average consumption rate of 1 kg/m².

INSTRUCTIONS

To carry out the work in a proper way, it is needed to strictly follow the

instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23 °C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.