

PRODUCT DATA SHEET

NITROLUX 20
Nitrosynthetic glossy enamel

CHARACTERISTIC Smalto di finitura lucido per esterno, pigmentato, adatto per manufatti in metallo, facilmente applicabile. È ideale per l'uso professionale in quanto dotato di potere riempitivo, adesione su fondi diversi e di un'essiccazione veloce che permette di ridurre i tempi di verniciatura. Forma una pellicola di finitura caratterizzata da elevata omogeneità estetica con buona resistenza al graffio e all'abrasione. È formulato con nitrocellulosa modificata e resine alchidiche speciali in fase solvente.

USE It is used in coating of metal items such as office furniture and shelving, applied directly to the properly cleaned and degreased iron. Under unfavorable conditions, due to excessive humidity or high temperatures, to avoid pitting or other flaws of the film, use thinner Diluente Butol. The product can also be applied by dipping, especially on turned parts. Spray application generally takes place waiting 15-20' between the layers with the technique of wet-on-wet.

PROPERTY OF THE PRODUCT	VALUE	METHOD
Application temperature	<+80 °C	
Flash point	27 °C	
Solid by volume	45 %± 2	

TECHNICAL DATA	VALUE	METHOD
Specific weight	950-1100 g/l	Internal PF3
Gloss	80-90	Internal PF6
Drying Time	Overcoatable 12h; Fully 5 days	Internal PF2

THICKNESS AND YIELD	Min.	Max	Recommended
Thickness of dry film, µm	35	45	40
Thickness of wet film, µm	80	100	90
Theoretical yield, m ² /l	12.5	10	11.1
Theoretical yield, m ² /kg	12.2	9.8	10.9

STORAGE Product is stable till one year as long as it is kept in original and unopened buckets at temperature between +5 °C e +30 °C.

COLOUR The range of colors can be chosen in shades of RAL. Between one production and the other, tint may be slightly different, it is therefore important to finish the job with the same batch.

PREPARATION OF SURFACE **General observation:** Surface must be dry and clean from any kind of oil, grease and salts.
Coated surface
With primer: it can be painted if the substrate is clean and free of dirt, oil, grease, and the application falls within the maximum re-coat time of the primer. If cleaning is required, perform pressure washing grade Wa 2 (surface free of oil,

PRODUCT DATA SHEET

NITROLUX 20
Nitrosynthetic glossy enamel

grease, salt, dirt).

With complete finishing coat: if undamaged compatible and non-chalky perform cleaning from any oil and grease with detergent, then run sanding surface followed by pressure washing to remove dust and salts.

Rusty coating: perform mechanical preparation St2 or St3 followed by pressure washing to remove oil, grease, dust and salt or sand blasting Sa2 or Sa2½; then restore the thickness of primer.

Localized maintenance: perform mechanical preparation St2 or St3 followed by pressure washing to remove oil, grease, dust and salt or sand blasting Sa2 or Sa2½. Round off the edges of the well anchored painting and restore the system in the original layers and thicknesses.

TOOLS

Conventional or airless spray: Nitro NV 5000 (with high temperature and humidity <40% it is possible the formation of "dusting"); in this case use Diluente Butol.

APPLICATION

Thinning	5-10% with Diluente Nitro NV5000
Application condition	+5°C +40°C >3°C at dew point Relative humidity: < 70%
Application by airless	Nozzle pressure: 15 MPa (150 kp/cm ² , 2100 psi). Nozzle: 0,28 - 0,38 mm (0,011 - 0,018") Angle range: 40 - 80° Air pressure: Compression ratio 30:1 (pressure 150-180 kg/cm ²)
Application by conventional spray	Nozzle: 1,6 - 1,8 mm Angle range: 40 - 80° Air pressure: 3,5-4 kg/cm ²
Thinner for washing	Diluente Nitro NV 5000

DRYING TIME

Dry time are purely indicative as it might be longer or shorter by keeping in consideration ventilation, humidity, thickness of the applied film. High thicknesses per coat and unfavorable environmental conditions slow down the drying and hardening depth.

DTF 40 micron

Surface temperature	10°C	23°C
Out touch	45'	30'
Dry touch	8h	4h
Full	7 days	5 days
Minimum time of over application	16h	12h

PRODUCT DATA SHEET

NITROLUX 20
Nitrosynthetic glossy enamel

 RECOMMENDED
 PRIMER

 Steel: Galvanized steel, aluminum, alloys: Primer 40
 Primer 15, Primer 40

 RECOMMENDED
 SYSTEM

Product	Coat	Wet Thickness	Dry thickness
Primer 15	1	100	60
Nitrolux 20	1	90	40
Total	2	190	100

 ALTERNATIVE
 SYSTEM

Product	Coat	Wet Thickness	Dry thickness
Primer 40	1	109	60
Nitrolux 20	1	90	40
Total	2	199	100

INSTRUCTIONS

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system may vary.

This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample.