

## DESCRIPTION

A colourless wall primer, formulated with water-dispersed synthetic resins with a special technology that allows for a special filming, which guarantees secure adhesion on different types of substrate. Thanks to its insulating capacity, it guarantees homogeneous absorption and therefore a uniform finish, with excellent adhesion of subsequent paints.

It is mainly formulated for siloxane treatments.

## PRODUCT PROPERTY

	<b>Value</b>	<b>Method</b>
<b>Adhesion to substrates in building</b>	GOOD	
<b>Water vapour permeability</b>	EXCELLENT	
<b>Drying time</b>	Recoatable 5-8h	Internal PF2
<b>Solid by weight</b>	7-10 %	Internal PF25

## PERFORMANCE DATA

	<b>Value</b>	<b>Method</b>
<b>Specific weight</b>	950-1050 g/l	Internal PF3

## SHELF LIFE

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

## COLOUR RANGE

Colourless

## TYPICAL USE

Directly as a preventive coat on old paintwork and alkaline substrates such as plaster of various compositions (cement, lime-based, pre-mixed, skim coat), concrete and fibre cement in a single coat. Can be overcoated with siloxane water-based paints from the Fasadecap range.

## TOOLS

Roller, Brush, Spray.

## THINNING

Ready to use

## COVERAGE

8-10 m<sup>2</sup>/l per coat.

## APPLY

+5°C +30°C

## SPECIFICATION ITEM

Colourless siloxanic masonry primer in water dispersion ideal as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat, at an average consumption rate of 110 ml/m<sup>2</sup>. Can be recoated with siloxanic water paints such as *Sil*.

## INSTRUCTIONS

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.